



Calorimetric glass transition in vitreous Silica

Yue, Yuanzheng

Published in:

21st International Congress on Glass - Abstract Book

Publication date:

2007

Document Version

Publisher's PDF, also known as Version of record

[Link to publication from Aalborg University](#)

Citation for published version (APA):

Yue, Y. (2007). Calorimetric glass transition in vitreous Silica. In 21st International Congress on Glass - Abstract Book (pp. 199-199). International Commission on Glass.

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal -

Take down policy

If you believe that this document breaches copyright please contact us at vbn@aub.aau.dk providing details, and we will remove access to the work immediately and investigate your claim.

Calorimetric Glass Transition in Vitreous Silica

Yuanzheng Yue

Section of Chemistry, Aalborg University, Denmark

The glass transition is one of the important topics for condensed matter research. Though considerable progress has been made in understanding the glass transition in general, some crucial questions still remain unanswered. One of these questions is related to the anomalous features of glass transition in vitreous silica. By performing differential scanning calorimetric (DSC) experiments, I have observed new anomalous features of the calorimetric glass transition of vitreous silica besides those known in literature. First, the shape of the heat capacity jump from glassy to liquid state becomes distorted after a certain number of the DSC scans (up to 1350 °C). Second, the onset glass transition temperature (T_g) decreases with increasing number of DSC scans, and reaches a constant value after a certain number of DSC scans. Third, there is a striking difference in the shape of the glass transition peak between bulk and fiber vitreous silica, even if they both undergo the same thermal history prior to calorimetric scans. These features, along with high sensitivity of the T_g to hydroxyl content, are probably the main reasons why there is still lack of a generally accepted T_g value for the vitreous silica in the glass community. By considering the above-mentioned anomalous features I suggest an approach for determining the standard T_g of vitreous silica. The origin of those features of vitreous silica is discussed from the energetic and the structural aspects.